

Rev Jan 2013

Data Sheet: 1012 INTERLEAVED 30 MICRON ALUMINIUM TAPE

TECHNICAL DETAILS	TYPICAL VALUE	UNITS
Thickness, foil carrier + adhesive thickness	0.070 0.030	mm mm
Adhesive Type	Rubber resin	
Peel adhesion: Open Side Closed Side	1000 1000	N/m N/m
Polyester Loop Tack: Open Side Closed Side	900 900	N/m N/m
Release from Liner Tensile Strength Elongation at break Service Temperature Range	10 1500 3 -10 to +60	N/m N/m % °C
Recommended Application Temperature Shear adhesion, 1 Kg @ 23 °C Shelf Life	+5 to +25 15 12	°C Hours Months

Test Methods: BS 3924

Important Notice

All GSAP products are subjected to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning GSAP products is based upon research, which the Company believes to be reliable, but some information does not constitute a warranty. Because of the variety of possible uses for GSAP products and continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential damages. All specifications are subject to change without prior notice.