



REV: SEPT 2016

Data Sheet: 7001 Double Sided Tissue Tape - Solvent Acrylic Adhesive

<u>Technical Details</u>	<u>Typical Value</u>	<u>Units</u>
Thickness, adhesive + carrier	0.15	mm
Release liner thickness	0.12	mm
180 degree peel adhesion:		
Open side	700	N/m
Closed side	700	N/m
Polyester loop tack:		
Open side	800	N/m
Closed side	800	N/m
Liner release	10	N/m
Tensile strength	1000	N/m
Elongation at break	4	%
Service temperature, continuous	-40 to +140	Deg C
Adhesive	Acid free	Internal test
Temperature exposure short term	200 < 1min	Deg C
Plasticizer resistance		Excellent
Recommended application temperature	+5 to +25	Deg C
Shear adhesion, 1kg @23 deg c	50	Hours
Shelf life	12	Months
FDA approval	175.105	FDA

Important Notice

All GSAP products are subjected to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning GSAP products is based upon research, which the Company believes to be reliable, but some information does not constitute a warranty. Because of the variety of possible uses for GSAP products and continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential damages. All specifications are subject to change without prior notice.